

Table 1 – Asphalt Mixes for Wearing Course

Item	Technical Class of the Road	Technical Category of the Street	Type and symbol of the asphalt mix ⁽¹⁾
1	I	I	Asphalt mix reinforced with fibres: MASF 8; MASF 16
			Asphalt mix with modified bitumen, reinforced with fibres: MASF 8 m; MASF 16 m
			Asphalt concrete with modified bitumen, BA 16 m
			Rough asphalt concrete <ul style="list-style-type: none"> - with modified bitumen, BAR 16 m; - with pure bitumen, BAR 16
2	II, III	II, III	Asphalt mix reinforced with fibres: MASF 8, MAF 16
			Asphalt mix with modified bitumen, reinforced with fibres: MASF 8 m; MASF 16 m
			Rough asphalt concrete <ul style="list-style-type: none"> - with modified bitumen, BAR 16 m; - with pure bitumen, BAR 16
			Asphalt concrete <ul style="list-style-type: none"> - with modified bitumen, BAR 16 m; - with pure bitumen, BAR 16
3	IV, V	IV	Asphalt concrete: with pure bitumen, BA 8; BA 16; BA 25
			Asphalt concrete: with gravel mixed with pure bitumen, BACP 16
⁽¹⁾ If the bitumen adhesivity on the used natural aggregates is below the 80% limit, the bitumen will be additivated with an additive that improves its adhesivity.			